

Carbon Black N-991

TECHNICAL SPECIFICATION

QUALITY PARAMETER	VALUE	TEST METHOD
Iodine adsorption number [g/kg]	9±3	ASTM D 1510
Oil absorption number [cm ³ /100g]	42±5	ASTM D 2414
pH-value	7-11	ASTM D 1512
Heating loss at 125°C [%], max.	0.4	ASTM D 1509
Ash content [%], max.	0.2	ASTM D 1506
Sieve residue: 0.045 [%], max.	0.08	ASTM D 1514

Note: The above-mentioned values do not constitute a specification or certification for a particular shipment, but merely represent values, based on analysis of spot samples from previous productions.

Release 19.05.2017